



NSAI
Standards

Irish Standard
I.S. EN ISO 6892-1:2019

Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2019)

© CEN 2019 No copying without NSAI permission except as permitted by copyright law.

I.S. EN ISO 6892-1:2019

Incorporating amendments/corrigenda/National Annexes issued since publication:

The National Standards Authority of Ireland (NSAI) produces the following categories of formal documents:

I.S. xxx: Irish Standard — national specification based on the consensus of an expert panel and subject to public consultation.

S.R. xxx: Standard Recommendation — recommendation based on the consensus of an expert panel and subject to public consultation.

SWiFT xxx: A rapidly developed recommendatory document based on the consensus of the participants of an NSAI workshop.

This document replaces/revises/consolidates the NSAI adoption of the document(s) indicated on the CEN/CENELEC cover/Foreword and the following National document(s):

NOTE: The date of any NSAI previous adoption may not match the date of its original CEN/CENELEC document.

This document is based on:

EN ISO 6892-1:2019

Published:

2019-12-04

This document was published under the authority of the NSAI and comes into effect on:

2019-12-23

ICS number:

77.040.10

NOTE: If blank see CEN/CENELEC cover page

NSAI
1 Swift Square,
Northwood, Santry
Dublin 9

T +353 1 807 3800
F +353 1 807 3838
E standards@nsai.ie
W NSAI.ie

Sales:
T +353 1 857 6730
F +353 1 857 6729
W standards.ie

Údarás um Chaighdeáin Náisiúnta na hÉireann

National Foreword

I.S. EN ISO 6892-1:2019 is the adopted Irish version of the European Document EN ISO 6892-1:2019, Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2019)

This document does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

For relationships with other publications refer to the NSAI web store.

Compliance with this document does not of itself confer immunity from legal obligations.

In line with international standards practice the decimal point is shown as a comma (,) throughout this document.

This is a free 15 page sample. Access the full version online.

This page is intentionally left blank

EUROPEAN STANDARD

EN ISO 6892-1

NORME EUROPÉENNE

EUROPÄISCHE NORM

December 2019

ICS 77.040.10

Supersedes EN ISO 6892-1:2016

English Version

Metallic materials - Tensile testing - Part 1: Method of test at room temperature (ISO 6892-1:2019)

Matériaux métalliques - Essai de traction - Partie 1:
Méthode d'essai à température ambiante (ISO 6892-
1:2019)

Metallische Werkstoffe - Zugversuch - Teil 1:
Prüfverfahren bei Raumtemperatur (ISO 6892-1:2019)

This European Standard was approved by CEN on 12 November 2019.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

CEN-CENELEC Management Centre: Rue de la Science 23, B-1040 Brussels

Contents

Page

European foreword..... 3

This is a free 15 page sample. Access the full version online.

European foreword

This document (EN ISO 6892-1:2019) has been prepared by Technical Committee ISO/TC 164 "Mechanical testing of metals" in collaboration with Technical Committee CEN/TC 459/SC 1 "Test methods for steel (other than chemical analysis)" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2020, and conflicting national standards shall be withdrawn at the latest by June 2020.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 6892-1:2016.

According to the CEN-CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Republic of North Macedonia, Romania, Serbia, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

Endorsement notice

The text of ISO 6892-1:2019 has been approved by CEN as EN ISO 6892-1:2019 without any modification.

This is a free 15 page sample. Access the full version online.

This page is intentionally left blank

**Metallic materials — Tensile testing —
Part 1:
Method of test at room temperature**

*Matériaux métalliques — Essai de traction —
Partie 1: Méthode d'essai à température ambiante*





COPYRIGHT PROTECTED DOCUMENT

© ISO 2019

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword.....	v
Introduction.....	vi
1 Scope.....	1
2 Normative references.....	1
3 Terms and definitions.....	1
4 Symbols.....	6
5 Principle.....	8
6 Test pieces.....	8
6.1 Shape and dimensions.....	8
6.1.1 General.....	8
6.1.2 Machined test pieces.....	9
6.1.3 Unmachined test pieces.....	9
6.2 Types.....	9
6.3 Preparation of test pieces.....	10
7 Determination of original cross-sectional area.....	10
8 Original gauge length and extensometer gauge length.....	10
8.1 Choice of the original gauge length.....	10
8.2 Marking the original gauge length.....	10
8.3 Choice of the extensometer gauge length.....	11
9 Accuracy of testing apparatus.....	11
10 Conditions of testing.....	11
10.1 Setting the force zero point.....	11
10.2 Method of gripping.....	11
10.3 Testing rates.....	12
10.3.1 General information regarding testing rates.....	12
10.3.2 Testing rate based on strain rate (method A).....	12
10.3.3 Testing rate based on stress rate (method B).....	14
10.3.4 Report of the chosen testing conditions.....	15
11 Determination of the upper yield strength.....	16
12 Determination of the lower yield strength.....	16
13 Determination of proof strength, plastic extension.....	16
14 Determination of proof strength, total extension.....	17
15 Method of verification of permanent set strength.....	17
16 Determination of the percentage yield point extension.....	17
17 Determination of the percentage plastic extension at maximum force.....	17
18 Determination of the percentage total extension at maximum force.....	18
19 Determination of the percentage total extension at fracture.....	18
20 Determination of percentage elongation after fracture.....	18
21 Determination of percentage reduction of area.....	19
22 Test report.....	20
23 Measurement uncertainty.....	20
23.1 General.....	20
23.2 Test conditions.....	21
23.3 Test results.....	21

Annex A (informative) Recommendations concerning the use of computer-controlled tensile testing machines	34
Annex B (normative) Types of test pieces to be used for thin products: sheets, strips, and flats between 0,1 mm and 3 mm thick	40
Annex C (normative) Types of test pieces to be used for wire, bars, and sections with a diameter or thickness of less than 4 mm	43
Annex D (normative) Types of test pieces to be used for sheets and flats of thickness equal to or greater than 3 mm and wire, bars, and sections of diameter or thickness equal to or greater than 4 mm	44
Annex E (normative) Types of test pieces to be used for tubes	48
Annex F (informative) Estimation of the crosshead separation rate in consideration of the stiffness (or compliance) of the testing equipment	50
Annex G (normative) Determination of the modulus of elasticity of metallic materials using a uniaxial tensile test	52
Annex H (informative) Measuring the percentage elongation after fracture if the specified value is less than 5 %	61
Annex I (informative) Measurement of percentage elongation after fracture based on subdivision of the original gauge length	62
Annex J (informative) Determination of the percentage plastic elongation without necking, A_{wn}, for long products such as bars, wire, and rods	64
Annex K (informative) Estimation of the uncertainty of measurement	65
Annex L (informative) Precision of tensile testing — Results from interlaboratory programmes ..	69
Bibliography	76

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular, the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation of the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 164, *Mechanical testing of metals*, Subcommittee SC 1, *Uniaxial testing*.

This third edition cancels and replaces the second edition (ISO 6892-1:2016), of which it constitutes a minor revision. The changes compared to the previous edition are as follows:

- correction of the title of a standard in [Clause 2](#);
- correction of the designation "coefficient of determination" ("coefficient of determination" instead of "coefficient of correlation");
- correction of [Formula \(1\)](#);
- wording in [10.3.2.1](#);
- wording in the key of [Figure 9](#);
- wording in [Table B.2](#);
- wording in [Table D.3](#);
- correction of the references.

A list of all parts in the ISO 6892 series can be found on the ISO website.

Any feedback or questions on this document should be directed to the user's national standards body. A complete listing of these bodies can be found at www.iso.org/members.html.

Introduction

During discussions concerning the speed of testing in the preparation of ISO 6892, it was decided to recommend the use of strain rate control in future revisions.

In this document, there are two methods of testing speeds available. The first, method A, is based on strain rates (including crosshead separation rate) and the second, method B, is based on stress rates. Method A is intended to minimize the variation of the test rates during the moment when strain rate sensitive parameters are determined and to minimize the measurement uncertainty of the test results. Therefore, and out of the fact that often the strain rate sensitivity of the materials is not known, the use of method A is strongly recommended.

NOTE In what follows, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, are used on various occasions (as figure axis labels or in explanations for the determination of different properties). However, for a general description or point on a curve, the designations “force” and “stress” or “extension”, “percentage extension”, and “strain”, respectively, can be interchanged.

Metallic materials — Tensile testing —

Part 1: Method of test at room temperature

1 Scope

This document specifies the method for tensile testing of metallic materials and defines the mechanical properties which can be determined at room temperature.

NOTE [Annex A](#) contains further recommendations for computer controlled testing machines.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 7500-1, *Metallic materials — Calibration and verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials — Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- ISO Online browsing platform: available at <https://www.iso.org/obp>
- IEC Electropedia: available at <http://www.electropedia.org/>

3.1 gauge length

L

length of the parallel portion of the test piece on which elongation is measured at any moment during the test

3.1.1 original gauge length

L_0

length between *gauge length* (3.1) marks on the test piece measured at room temperature before the test

3.1.2 final gauge length after fracture

L_u

length between *gauge length* (3.1) marks on the test piece measured after rupture, at room temperature, the two pieces having been carefully fitted back together so that their axes lie in a straight line

This is a free preview. Purchase the entire publication at the link below:

I.S. EN ISO 6892-1 : 2019 : EN : COMBINED PDF

- ⤵ Looking for additional Standards? Visit SAI Global Infostore
- ⤵ Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation

Need to speak with a Customer Service Representative - Contact Us